



ANH Refractories Europe Ltd

Dock Road South, Bromborough
Wirral, England, CH62 4SP
Tel +44 (0)151 641 5900
Fax +44 (0)151 641 5910
Email sales@anheurope.co.uk
Web www.anheurope.co.uk

Mixing & Using Instructions

ULTRAGREEN SR

General

Material should be stored in a dry place. For best results, material should be maintained at 10 - 21°C prior to casting.

Porous back-up materials or wood forms should be waterproofed. Absorption of water can result in reduced flow, or affect the hydraulic set. Forms must be stout and water tight.

This product is designed to be mixed with water and vibra-cast. All equipment used to mix this product must be clean.

Never mix less than full bags. For best results, water should be maintained at 10 - 21°C.

Water Addition and Mixing Requirements

Water addition per 100 Kg 4.0 – 5.0 Litres

Mix for at least five minutes. For best results, wet mix temperature should be maintained at 15 - 25°C. Minor adjustments to the amount of water are permissible to achieve desired flow, avoid using water additions in excess of that required to produce adequate flow characteristics.

Installation

Install within 20 minutes of adding water. For best results use a 50 – 60 mm diameter high frequency (14000 cpm) immersion vibrator and vibrate thoroughly to remove air pockets. Do not trowel to slick finish. At temperatures above 20°C, air cure, keeping surfaces damp and / or covered, for 16 – 48 hours typically or until a hard set has developed. Lower temperatures will increase the time before a hard set develops. The best results are achieved at curing temperatures of 30°C - 45°C. Keep material from freezing during air cure and preferably until a dryout can be initiated. Freezing of this product prior to water removal can cause structural damage.



ANH Refractories Europe Ltd

Dock Road South, Bromborough
Wirral, England, CH62 4SP
Tel +44 (0)151 641 5900
Fax +44 (0)151 641 5910
Email sales@anheurope.co.uk
Web www.anheurope.co.uk

Dryout Schedule

Heating and cooling refractory structures can be a complex procedure and where possible should be delegated to experts. Where this is done by the client they are themselves contractually responsible, and the following is given in good faith for guidance only.

Ambient to 120°C	25°C / hour
Hold at 120°C for 60 mins per 25mm thickness	
120°C to 315°C	25°C / hour
Hold at 315°C for 60 mins per 25mm thickness	
315°C to 540°C	25°C / hour
Hold at 540°C for 60 mins per 25mm thickness	
540°C to operating temperature	55°C / hour

Never enclose a castable in a vapour-tight encasement as a dangerous steam explosion may result.

For thicknesses greater than 230mm or for multi-component linings contact ANH Refractories Europe Ltd for further advice.

Please note, the position of the control thermocouples for the heating and holding phase is important and can be critical. Advice can be given in good faith on request.

